

### Qualification Results Summary of AD623 Die Revision in SOIC\_N Package

QUALIFICATION RESULTS			
TEST	SPECIFICATION	SAMPLE SIZE	RESULTS
High Temperature Operating Life (HTOL)	JEDEC <i>JESD22-A108</i>	<b>9x77</b>	<b>Pass</b>
Highly Accelerated Stress Test (HAST)*	JEDEC <i>JESD22-A110</i>	<b>9x77</b>	<b>Pass</b>
Temperature Cycle (TC)*	JEDEC <i>JESD22-A104</i>	<b>9x77</b>	<b>Pass</b>
High Temperature Storage Life (HTSL)	JEDEC <i>JESD22-A103</i>	<b>3x77</b>	<b>Pass</b>
Solder Heat Resistance (SHR)*	JEDEC/IPC <i>J-STD-020</i>	<b>3x11</b>	<b>Pass</b>
Latch-Up	JEDEC <i>JESD78</i>		<b>Pass</b>
Electrostatic Discharge <i>Human Body Model</i>	ESDA/JEDEC <i>JS-001</i>	<b>3/voltage</b>	<b>Pass 4000V</b>
Electrostatic Discharge <i>Field-Induced Charged Device Model</i>	JEDEC <i>JESD22-C101</i>	<b>3/voltage</b>	<b>Pass 1250V</b>

\*These samples were subjected to preconditioning (per J-STD-020 Level 1) prior to the start of the stress test. Level 1 preconditioning consists of the following: 1. Bake – 24 hours at 125°C; 2. Soak – unbiased soak for 168 hours at 85C, 85%RH; 3. Reflow – three passes through a reflow oven with a peak temperature of 260°C.

## Qualification Results Summary of AD623 Die Revision in MSOP Package

QUALIFICATION RESULTS			
TEST	SPECIFICATION	SAMPLE SIZE	RESULTS
High Temperature Operating Life (HTOL)	JEDEC <i>JESD22-A108</i>	<b>9x77</b>	<b>Pass</b>
Highly Accelerated Stress Test (HAST)*	JEDEC <i>JESD22-A110</i>	<b>9x77</b>	<b>Pass</b>
Temperature Cycle (TC)*	JEDEC <i>JESD22-A104</i>	<b>9x77</b>	<b>Pass</b>
High Temperature Storage Life (HTSL)	JEDEC <i>JESD22-A103</i>	<b>3x77</b>	<b>Pass</b>
Solder Heat Resistance (SHR)*	JEDEC/IPC <i>J-STD-020</i>	<b>3x11</b>	<b>Pass</b>
Latch-Up	JEDEC <i>JESD78</i>		<b>Pass</b>
Electrostatic Discharge <i>Human Body Model</i>	ESDA/JEDEC <i>JS-001</i>	<b>3/voltage</b>	<b>Pass 4000V</b>
Electrostatic Discharge <i>Field-Induced Charged Device Model</i>	JEDEC <i>JESD22-C101</i>	<b>3/voltage</b>	<b>Pass 1250V</b>

\*These samples were subjected to preconditioning (per J-STD-020 Level 1) prior to the start of the stress test. Level 1 preconditioning consists of the following: 1. Bake – 24 hours at 125°C; 2. Soak – unbiased soak for 168 hours at 85C, 85%RH; 3. Reflow – three passes through a reflow oven with a peak temperature of 260°C.