



AHEAD OF WHAT'S POSSIBLE™

# DISPLACEMENT DAMAGE TEST REPORT OP484S

January 2023



## Radiation Test Report

Product:	OP484S
Die:	1447Z
Fluence:	2e12 n/cm <sup>2</sup>
Test Method:	MIL-STD-883 TM1017
Facilities:	UMass Lowell
Tested:	January 5, 2023

The RADTEST® DATA SERVICE is a compilation of radiation test results on Analog Devices' Space grade products. It is designed to assist customers in selecting the right product for applications where radiation is a consideration. Many products manufactured by Analog Devices, Inc. have been shown to be radiation tolerant to most tactical radiation environments. Analog Devices, Inc. does not make any claim to maintain or guarantee these levels of radiation tolerance without lot qualification test.

It is the responsibility of the Procuring Activity to screen products from Analog Devices, Inc. for compliance to Nuclear Hardness Critical Items (HCI) specifications.

### Warning:

Analog Devices, Inc. does not recommend use of this data to qualify other product grades or process levels. Analog Devices, Inc. is not responsible and has no liability for any consequences, and all applicable Warranties are null and void if any Analog Devices product is modified in any way or used outside of normal environmental and operating conditions, including the parameters specified in the corresponding data sheet. Analog Devices, Inc. does not guarantee that wafer manufacturing is the same for all process levels.

Wafer	SN	ISY @ VS=+5V (A)			Vos (A) (V)			Vos (B) (V)			Vos (C) (V)		
		Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12
CTRL	82	3.76E-03	3.76E-03	3.75E-03	-8.27E-05	-8.36E-05	-8.35E-05	-1.22E-04	-1.22E-04	-1.20E-04	-1.36E-05	-1.46E-05	-1.03E-05
	86	3.75E-03	3.69E-03	3.64E-03	-1.31E-04	-1.55E-04	-1.51E-04	-1.11E-05	-1.34E-05	9.87E-06	-5.96E-06	-9.85E-06	-1.29E-05
	87	3.72E-03	3.66E-03	3.62E-03	-7.08E-05	-4.61E-05	-4.38E-05	-1.55E-05	-2.00E-05	-1.77E-05	-4.31E-05	-4.46E-05	-4.31E-05
	88	3.71E-03	3.65E-03	3.61E-03	-5.82E-05	-6.10E-05	-6.42E-05	4.54E-05	1.40E-05	-1.53E-06	-4.21E-05	-4.27E-05	-6.73E-05
	89	3.75E-03	3.69E-03	3.65E-03	-8.08E-05	-5.73E-05	-8.40E-05	-5.00E-05	-6.04E-05	-7.00E-05	-4.79E-05	-5.46E-05	-4.87E-05
	90	3.75E-03	3.68E-03	3.64E-03	-5.32E-05	-7.77E-05	-7.38E-05	-6.07E-07	-2.41E-05	1.15E-06	-4.40E-05	-4.91E-05	-4.51E-05
	91	3.88E-03	3.83E-03	3.78E-03	-4.16E-05	-3.99E-05	-5.13E-05	-3.30E-05	-1.04E-06	1.82E-06	-1.03E-04	-1.17E-04	-1.26E-04
	92	3.76E-03	3.70E-03	3.66E-03	-7.49E-05	-8.39E-05	-6.85E-05	-1.82E-05	-1.33E-05	-8.80E-06	-3.12E-05	-4.80E-05	-2.32E-05
	93	3.78E-03	3.72E-03	3.68E-03	5.31E-06	9.22E-06	1.34E-05	-1.49E-05	-3.65E-05	-4.40E-05	-3.16E-05	-6.10E-05	-9.09E-05
	94	3.80E-03	3.74E-03	3.70E-03	-3.01E-05	-3.24E-06	4.27E-06	-3.75E-05	-7.13E-05	-6.11E-05	-3.63E-05	-3.95E-05	-5.35E-05
	95	3.89E-03	3.83E-03	3.79E-03	-5.32E-05	-6.97E-05	-7.60E-05	-2.15E-05	-3.00E-05	-2.58E-05	-7.34E-05	-8.18E-05	-6.44E-05
	min	3.71E-03	3.65E-03	3.61E-03	-1.31E-04	-1.55E-04	-1.51E-04	-5.00E-05	-7.13E-05	-7.00E-05	-1.03E-04	-1.17E-04	-1.26E-04
	max	3.89E-03	3.83E-03	3.79E-03	5.31E-06	9.22E-06	1.34E-05	4.54E-05	1.40E-05	9.87E-06	-5.96E-06	-9.85E-06	-1.29E-05
	stdev	6.22E-05	6.26E-05	6.22E-05	3.56E-05	4.55E-05	4.62E-05	2.58E-05	2.57E-05	2.80E-05	2.62E-05	2.82E-05	3.26E-05
	average	3.78E-03	3.72E-03	3.68E-03	-5.88E-05	-5.80E-05	-5.95E-05	-1.57E-05	-2.56E-05	-2.16E-05	-4.59E-05	-5.48E-05	-5.75E-05
	+3 Sigma	3.97E-03	3.91E-03	3.86E-03	4.80E-05	7.86E-05	7.91E-05	6.16E-05	5.15E-05	6.24E-05	3.28E-05	2.99E-05	4.04E-05
	-3 Sigma	3.59E-03	3.53E-03	3.49E-03	-1.66E-04	-1.95E-04	-1.98E-04	-9.30E-05	-1.03E-04	-1.06E-04	-1.25E-04	-1.40E-04	-1.55E-04

Wafer	SN	Vos (D) (V)			Ios (A) (A)			Ios (B) (A)			Ios (C) (A)		
		Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12
CTRL	82	-7.31E-05	-7.34E-05	-7.30E-05	5.65E-09	4.88E-09	5.45E-09	-7.23E-11	-2.10E-10	-2.82E-10	-2.80E-09	-2.83E-09	-2.84E-09
	86	-1.23E-04	-1.02E-04	-8.47E-05	3.73E-09	6.18E-09	1.34E-08	4.13E-09	2.84E-08	2.19E-08	-1.32E-10	3.36E-09	4.37E-09
	87	-6.35E-05	-7.65E-05	-9.10E-05	6.83E-09	1.16E-08	2.36E-08	3.52E-09	-2.58E-09	8.96E-09	-5.16E-09	-6.97E-10	1.38E-08
	88	-6.89E-05	-3.56E-05	-1.68E-05	3.93E-09	-3.11E-09	-1.09E-08	2.78E-09	-1.11E-08	-1.33E-08	-6.16E-09	-1.22E-08	-7.99E-09
	89	-5.18E-05	-2.19E-05	-1.36E-05	5.77E-09	1.10E-08	4.51E-09	2.56E-09	-3.64E-09	-6.21E-09	-6.46E-10	-1.04E-09	1.62E-08
	90	-6.65E-05	-3.82E-05	-3.94E-05	2.65E-09	-4.93E-09	3.02E-09	3.11E-10	-2.57E-09	-4.37E-09	-3.20E-09	-5.33E-09	-1.58E-09
	91	-4.10E-05	-6.49E-05	-6.65E-05	2.87E-09	-9.62E-09	-2.23E-08	1.45E-09	8.20E-09	1.64E-08	-6.60E-09	-1.97E-08	-1.74E-08
	92	-9.69E-05	-9.77E-05	-8.95E-05	6.18E-09	-6.71E-09	-1.98E-08	-1.25E-09	-8.98E-09	-6.75E-09	6.72E-10	-8.83E-09	7.69E-09
	93	-8.50E-05	-7.65E-05	-8.17E-05	5.31E-09	1.39E-09	-3.18E-08	2.16E-09	8.88E-10	1.69E-09	1.30E-09	2.88E-10	6.18E-09
	94	-9.07E-05	-9.53E-05	-9.34E-05	5.48E-09	7.15E-09	1.44E-08	2.36E-09	4.95E-09	-6.94E-10	-3.82E-09	5.93E-09	-9.02E-09
	95	-8.65E-05	-6.73E-05	-4.00E-05	4.92E-09	-1.54E-08	-1.66E-08	2.29E-09	-2.21E-09	-1.13E-08	-8.46E-09	-1.04E-08	-5.41E-09
	min	-1.23E-04	-1.02E-04	-9.34E-05	2.65E-09	-1.54E-08	-3.18E-08	-1.25E-09	-1.11E-08	-1.33E-08	-8.46E-09	-1.97E-08	-1.74E-08
	max	-4.10E-05	-2.19E-05	-1.36E-05	6.83E-09	1.16E-08	2.36E-08	4.13E-09	2.84E-08	2.19E-08	1.30E-09	5.93E-09	1.62E-08
	stdev	2.44E-05	2.79E-05	3.14E-05	1.41E-09	9.15E-09	1.85E-08	1.55E-09	1.12E-08	1.17E-08	3.40E-09	7.91E-09	1.08E-08
	average	-7.43E-05	-6.76E-05	-6.17E-05	4.77E-09	-2.41E-10	-4.25E-09	2.03E-09	1.14E-09	6.37E-10	-3.21E-09	-4.86E-09	6.87E-10
	+3 Sigma	-1.03E-06	1.62E-05	3.26E-05	9.00E-09	2.72E-08	5.13E-08	6.69E-09	3.46E-08	3.58E-08	6.98E-09	3.18E-08	3.31E-08
	-3 Sigma	-1.48E-04	-1.51E-04	-1.56E-04	5.34E-10	-2.77E-08	-5.98E-08	-2.63E-09	-3.23E-08	-3.46E-08	-1.34E-08	-2.86E-08	-3.17E-08









Wafer	SN	Ios (D) (A)			+Ibias (A) (A)			+Ibias (B) (A)			+Ibias (C) (A)		
		Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12
CTRL	82	-7.96E-09	-7.95E-09	-8.04E-09	-1.86E-07	-1.36E-07	-1.36E-07	-1.41E-07	-1.42E-07	-1.41E-07	-1.45E-07	-1.45E-07	
	86	-4.05E-09	9.46E-09	3.50E-09	-1.62E-07	-2.81E-07	-3.38E-07	-1.32E-07	-2.33E-07	-3.15E-07	-1.49E-07	-2.75E-07	-3.50E-07
	87	-5.31E-09	-1.17E-08	1.18E-08	-1.42E-07	-2.62E-07	-3.21E-07	-1.39E-07	-2.49E-07	-3.09E-07	-1.45E-07	-2.67E-07	-3.29E-07
	88	-8.84E-09	-1.08E-08	-1.37E-08	-1.38E-07	-2.52E-07	-3.24E-07	-1.33E-07	-2.50E-07	-3.41E-07	-1.36E-07	-2.32E-07	
	89	-4.61E-09	1.46E-08	2.79E-08	-1.44E-07	-2.63E-07	-3.41E-07	-1.41E-07	-2.55E-07	-3.28E-07	-1.44E-07	-2.65E-07	-3.24E-07
	90	-6.90E-09	9.87E-09	1.46E-08	-1.46E-07	-2.65E-07	-3.35E-07	-1.36E-07	-2.70E-07	-3.27E-07	-1.39E-07	-2.67E-07	-3.43E-07
	91	-4.02E-09	-2.08E-08	-2.48E-08	-1.45E-07	-2.80E-07	-3.55E-07	-1.41E-07	-2.50E-07	-3.21E-07	-1.38E-07	-2.57E-07	-3.24E-07
	92	-4.18E-09	8.75E-09	2.57E-08	-1.34E-07	-2.62E-07	-3.39E-07	-1.18E-07	-2.36E-07	-3.06E-07	-1.46E-07	-2.80E-07	-3.47E-07
	93	-5.17E-09	-9.66E-09	-2.16E-08	-1.35E-07	-2.88E-07	-3.48E-07	-1.33E-07	-2.50E-07	-3.21E-07	-1.34E-07	-2.41E-07	-3.10E-07
	94	-5.28E-09	-7.87E-09	-1.31E-08	-1.39E-07	-2.67E-07	-3.21E-07	-1.33E-07	-2.35E-07	-3.08E-07	-1.38E-07	-2.36E-07	-3.08E-07
	95	-5.59E-09	-6.89E-09	-3.74E-08	-1.38E-07	-2.55E-07	-3.27E-07	-1.53E-07	-2.78E-07	-3.50E-07	-1.40E-07	-2.70E-07	-3.32E-07
	min	-6.90E-09	-2.08E-08	-3.74E-08	-1.62E-07	-2.81E-07	-3.55E-07	-1.53E-07	-2.78E-07	-3.50E-07	-1.49E-07	-2.80E-07	-3.50E-07
	max	-4.02E-09	1.46E-08	2.79E-08	-1.34E-07	-2.52E-07	-3.21E-07	-1.18E-07	-2.33E-07	-3.06E-07	-1.34E-07	-2.36E-07	-3.08E-07
	stdev	1.05E-09	1.20E-08	2.25E-08	7.89E-09	9.47E-09	1.18E-08	8.92E-09	1.46E-08	1.44E-08	4.79E-09	1.46E-08	1.43E-08
	average	-5.19E-09	-2.52E-09	-2.70E-09	-1.42E-07	-2.64E-07	-3.35E-07	-1.36E-07	-2.50E-07	-3.22E-07	-1.41E-07	-2.61E-07	-3.29E-07
	+3 Sigma	-2.06E-09	3.36E-08	6.49E-08	-1.19E-07	-2.36E-07	-3.00E-07	-1.09E-07	-2.07E-07	-2.79E-07	-1.27E-07	-2.17E-07	-2.86E-07
	-3 Sigma	-8.33E-09	-3.86E-08	-7.03E-08	-1.66E-07	-2.93E-07	-3.70E-07	-1.63E-07	-2.94E-07	-3.66E-07	-1.55E-07	-3.04E-07	-3.72E-07









Wafer	SN	-Ibias (D) (A)			-Ibias (A) (A)			-Ibias (B) (A)			-Ibias (C) (A)		
		Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12
CTRL	82	-1.50E-07	-1.50E-07	-1.49E-07	-1.41E-07	-1.41E-07	-1.41E-07	-1.41E-07	-1.41E-07	-1.41E-07	-1.42E-07	-1.43E-07	-1.42E-07
	86	-1.55E-07	-2.76E-07	-3.57E-07	-1.65E-07	-2.87E-07	-3.52E-07	-1.36E-07	-2.61E-07	-3.37E-07	-1.48E-07	-2.79E-07	-3.54E-07
	87	-1.48E-07	-2.84E-07	-3.40E-07	-1.49E-07	-2.73E-07	-3.44E-07	-1.42E-07	-2.46E-07	-3.18E-07	-1.40E-07	-2.66E-07	-3.43E-07
	88	-1.38E-07	-2.58E-07	-3.29E-07	-1.42E-07	-2.49E-07	-3.13E-07	-1.36E-07	-2.39E-07	-3.27E-07	-1.30E-07	-2.38E-07	-3.15E-07
	89	-1.26E-07	-2.37E-07	-3.05E-07	-1.49E-07	-2.74E-07	-3.46E-07	-1.44E-07	-2.51E-07	-3.22E-07	-1.43E-07	-2.64E-07	-3.40E-07
	90	-1.47E-07	-2.59E-07	-3.42E-07	-1.49E-07	-2.60E-07	-3.38E-07	-1.37E-07	-2.67E-07	-3.22E-07	-1.36E-07	-2.62E-07	-3.42E-07
	91	-1.47E-07	-2.76E-07	-3.54E-07	-1.48E-07	-2.70E-07	-3.33E-07	-1.43E-07	-2.58E-07	-3.37E-07	-1.32E-07	-2.37E-07	-3.07E-07
	92	-1.40E-07	-2.59E-07	-3.31E-07	-1.40E-07	-2.55E-07	-3.19E-07	-1.17E-07	-2.27E-07	-2.99E-07	-1.47E-07	-2.71E-07	-3.54E-07
	93	-1.40E-07	-2.54E-07	-3.25E-07	-1.41E-07	-2.59E-07	-3.16E-07	-1.35E-07	-2.51E-07	-3.23E-07	-1.35E-07	-2.41E-07	-3.16E-07
	94	-1.40E-07	-2.51E-07	-3.23E-07	-1.44E-07	-2.74E-07	-3.36E-07	-1.35E-07	-2.40E-07	-3.07E-07	-1.34E-07	-2.42E-07	-2.99E-07
	95	-1.42E-07	-2.48E-07	-									









Wafer	SN	-bias (D) (A)			AVO (A) (V/mV)			AVO (B) (V/mV)			AVO (C) (V/mV)		
		Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12
CTRL	82	-1.42E-07	-1.42E-07	-1.41E-07	454.00	467.95	454.74	437.89	451.68	441.51	418.68	418.52	417.24
	86	-1.51E-07	-2.86E-07	-3.60E-07	363.39	305.49	252.52	384.25	279.19	264.16	474.26	401.82	347.03
	87	-1.43E-07	-2.72E-07	-3.51E-07	360.67	363.37	310.51	386.58	368.63	289.55	411.44	330.08	290.95
	88	-1.31E-07	-2.47E-07	-3.15E-07	381.15	312.09	270.70	391.86	295.86	248.32	443.75	348.81	271.41
	89	-1.22E-07	-2.52E-07	-3.33E-07	411.94	388.61	349.88	381.03	349.59	282.52	433.84	377.83	323.96
	90	-1.40E-07	-2.69E-07	-3.57E-07	450.37	326.19	277.84	411.96	364.78	348.80	468.94	394.58	321.84
	91	-1.43E-07	-2.55E-07	-3.29E-07	453.21	427.31	324.64	497.16	425.47	370.04	467.68	376.28	282.53
	92	-1.36E-07	-2.68E-07	-3.57E-07	487.39	319.63	339.72	393.82	353.74	284.05	442.83	323.81	283.60
	93	-1.34E-07	-2.44E-07	-3.04E-07	410.45	322.47	332.73	421.62	311.77	264.72	471.95	393.37	315.66
	94	-1.35E-07	-2.43E-07	-3.10E-07	494.90	427.03	373.67	425.91	316.08	290.36	384.42	320.26	283.50
	95	-1.36E-07	-2.41E-07	-2.92E-07	501.48	377.62	357.54	514.14	415.78	349.35	507.44	407.29	344.34
	min	-1.51E-07	-2.86E-07	-3.60E-07	360.67	305.49	252.52	381.03	279.19	248.32	384.42	320.26	271.41
	max	-1.22E-07	-2.41E-07	-2.92E-07	501.48	427.31	373.67	514.14	425.47	370.04	507.44	407.29	347.03
	stdev	7.83E-09	1.52E-08	2.48E-08	53.63	46.57	40.27	47.49	48.45	41.74	35.24	33.73	27.49
	average	-1.37E-07	-2.58E-07	-3.31E-07	431.49	356.98	318.98	420.83	348.09	299.19	450.65	367.41	306.48
	+3 Sigma	-1.14E-07	-2.12E-07	-2.57E-07	592.38	496.70	439.79	563.31	493.43	424.39	556.37	468.60	388.94
	-3 Sigma	-1.61E-07	-3.03E-07	-4.05E-07	270.61	217.26	198.16	278.35	202.75	173.98	344.93	266.23	224.03

Wafer	SN	AVO (D) (V/mV)			VOH (A) (V)			VOH (B) (V)			VOH (C) (V)		
		Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12	Initial	1.00E+12	2.00E+12
CTRL	82	487.17	502.08	483.52	4.8756	4.8763	4.8748	4.8822	4.8827	4.8814	4.8786	4.8792	4.8779
	86	561.37	421.17	384.15	4.8781	4.8805	4.8778	4.8825	4.8826	4.8805	4.8794	4.8781	4.8767
	87	458.35	378.83	317.70	4.8767	4.8768	4.8776	4.8827	4.8825	4.8813	4.8795	4.8784	4.8778
	88	461.43	403.42	333.85	4.8765	4.8766	4.8768	4.8809	4.8809	4.8793	4.8773	4.8762	4.8755
	89	442.19	393.15	350.48	4.8758	4.8761	4.8764	4.8809	4.8798	4.8794	4.8774	4.8752	4.8758
	90	482.34	391.11	365.30	4.8754	4.8757	4.8761	4.8809	4.8808	4.8794	4.8770	4.8761	4.8755
	91	465.51	368.48	314.52	4.8757	4.8762	4.8764	4.8817	4.8824	4.8803	4.8782	4.8778	4.8761
	92	499.84	356.44	300.30	4.8768	4.8772	4.8772	4.8815	4.8816	4.8801	4.8775	4.8767	4.8759
	93	476.31	439.36	368.11	4.8771	4.8773	4.8771	4.8809	4.8811	4.8794	4.8768	4.8760	4.8753
	94	472.46	397.86	357.36	4.8751	4.8754	4.8756	4.8801	4.8803	4.8786	4.8762	4.8754	4.8744
	95	428.76	369.78	373.17	4.8739	4.8743	4.8751	4.8802	4.8805	4.8788	4.8762	4.8750	4.8743
	min	428.76	356.44	300.30	4.8739	4.8743	4.8751	4.8801	4.8798	4.8786	4.8762	4.8750	4.8743
	max	561.37	439.36	384.15	4.8781	4.8805	4.8778	4.8827	4.8826	4.8813	4.8795	4.8784	4.8778
	stdev	36.37	25.27	28.34	0.0012	0.0016	0.0009	0.0009	0.0010	0.0008	0.0012	0.0012	0.0010
	average	474.85	391.96	346.49	4.8761	4.8766	4.8766	4.8812	4.8813	4.8797	4.8776	4.8765	4.8757
	+3 Sigma	583.96	467.76	431.52	4.8797	4.8815	4.8792	4.8839	4.8842	4.8822	4.8810	4.8802	4.8789
	-3 Sigma	365.75	316.16	261.47	4.8725	4.8717	4.8740	4.8786	4.8783	4.8772	4.8741	4.8728	4.8727


Wafer	SN	VOH (D) (V)		
		Initial	1.00E+12	2.00E+12
CTRL	82	4.8760	4.8766	4.8751
	86	4.8755	4.8736	4.8740
	87	4.8765	4.8756	4.8751
	88	4.8756	4.8748	4.8740
	89	4.8743	4.8733	4.8733
	90	4.8741	4.8734	4.8729
	91	4.8732	4.8728	4.8726
	92	4.8745	4.8739	4.8734
	93	4.8730	4.8723	4.8723
	94	4.8728	4.8722	4.8717
	95	4.8725	4.8714	4.8715
	min	4.8725	4.8714	4.8715
	max	4.8765	4.8756	4.8751
	stdev	0.0013	0.0013	0.0011
	average	4.8742	4.8733	4.8731
	+3 Sigma	4.8782	4.8771	4.8765
	-3 Sigma	4.8702	4.8696	4.8697







VOH (D)



	Initial	1.00E+12	2.00E+12
Average	4.8742	4.8733	4.8731
-3 Sigma	4.8702	4.8696	4.8697
+3 Sigma	4.8782	4.8771	4.8765